



PARSON ADHESIVES, INC.

3345 Auburn Road Suite 107 Rochester, MI 48309

Phone (248) 299-5585 Fax (248) 299-3846 Email: sales@parsonadhesives.com

SONLOK™ 3515 **Anaerobic Gasket Sealant**

SONLOK 3515 is an anaerobic gasket sealant, which develops medium strength in a short time. The compound cures in the absence of air between close fitting metal surfaces.

SONLOK 3515 is a flexible gasketing sealant which will flex with minor flange movements. Provides resistance to low pressure immediately after assembly of flanges.

Applications:

- Typically used as a form-in-place gasket for pumps, thermostats, compressors, transmission housings and axle covers.
- Thixotropic nature reduces the migration of liquid product after application.

Adhesive Properties:

Composition:	Dimethacrylate ester
Color:	Purple
Viscosity:	275,000 to 950,000 cps Thixotropic
Brookfield RVT @ 25 °C Spindle 7 @ 20 rpm	
Specific Gravity:	1.10
Maximum Diameter of Thread/Gap Filling:	>0.50 mm
Flash Point:	> 93 °C
Solvent Content:	None

Curing Properties:

Handling Cure Time

Unprimed Surfaces:	1 to 2 hours
Primed Surfaces:	15 min. to 2 hours

Compressive Shear Strength:
(ISO 10123)

After 24 hours at 22 °C

Steel Pins & Collars	> 5 N/mm ² > 725 psi
----------------------	------------------------------------

Lap Shear Strength, ISO 4587
Steel (grit blasted)

6 N/mm²
870 psi



Tensile Strength, ISO 6922 14 N/mm²
Steel (grit blasted) 2,030 psi
Temperature Range -65 to 300 °F

Physical Properties:

Coefficient of Thermal Expansion, 80×10⁻⁶
ASTM D 696, K-1
Coefficient of Thermal Conductivity, 0.10
ASTM C 177, W/(m·K)
Specific Heat, kJ/(kg·K) 0.30

Chemical Resistance:

Chemical	Temp.	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22 °C	100	95
Ethanol	22 °C	90	85
Motor Oil	125 °C	160	165
Gasoline	22 °C	20	15
Brake Fluid	22 °C	95	95
Water/Glycol	87 °C	80	80

Directions for use:

- For best results, clean all surfaces (external and internal) with a cleaning solvent and allow solvent to evaporate.
- If the material is an inactive metal or the cure speed is too slow, spray with Activator 3071 or 3049 and allow to dry.
- Apply manually as a continuous bead or by screen-printing to one of surface of the flanges.
- Low pressure can be used when testing to confirm a complete seal immediately after assembly.
- Flanges should be tighten as soon as possible after assembly to avoid shimming.

Storage:

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 46 °F to 82 °F. Please do not return any unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

Warranty: All products purchased from or supplied by Parson are subject to terms and conditions set out in the contract. Parson warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Parson is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Parson makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.