



## PARSON ADHESIVES, INC.

3345 Auburn Road Suite 107 Rochester, MI 48309

Phone (248) 299-5585 Fax (248) 299-3846 Email: [sales@parsonadhesives.com](mailto:sales@parsonadhesives.com)

---

### **SONLOK™ 3660** **Retaining Compound**

SONLOK 3660 is a fast curing; paste like consistency, high strength anaerobic retaining compound for cylindrical fitting parts particularly where bond gaps can approach 0.50mm. This product offers very good gap cure properties.

SONLOK 3660 retaining compound is a single component anaerobic adhesive, which develops high strength rapidly when confined in the absence of air between close fitting metal surfaces to prevent loosening and leakage from shock and vibration.

#### **Applications:**

- Ideal to fill gaps up to 0.50 mm diameter clearance.
- Used for restoring correct fits on worn shafts, spun bearings and damaged keyways.
- Excellent retaining, sealing and thread locking compound.

#### **Adhesive Properties:**

Composition:	Urethane Methacrylate
Color:	Grey
Viscosity:	1, 225,000 cps at 25 °C
Brookfield HBT	
Specific Gravity:	1.13
Maximum Diameter of Thread/Gap Filling:	0.50 mm
Flash Point:	> 93 °C
Solvent Content:	None
Shelf Life:	1 year

#### **Curing Properties:**

Handling Cure Time:	10 minutes
Functional Cure Time:	2 - 3 hours
Full Cure Time:	24 hours
Compressive Shear Strength: (ISO 10123)	
<b>After 24 hours at 22 °C</b>	
Steel Pins & Collars	> 22 N/mm <sup>2</sup> > 3,100 psi
<b>After 30 minutes at 22 °C</b>	
Steel Pins & Collars	>15 N/mm <sup>2</sup> 2,000 psi
Temperature Range	-55 to 150 °C



## Physical Properties:

Coefficient of Thermal Expansion, ASTM D 696, K-1	80×10 <sup>-6</sup>
Coefficient of Thermal Conductivity, ASTM C 177,W/(m·K)	0.10
Specific Heat, kJ/(kg·K)	0.30

## Chemical Resistance:

Chemical	Temp.	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22 °C	100	95
Ethanol	22 °C	100	100
Motor Oil	125 °C	100	100
Gasoline	22 °C	100	100
Brake Fluid	22 °C	100	100
Water/Glycol	87 °C	100	98

## Directions for use:

### For Assembly

- For best results, clean all surfaces (external and internal) with a cleaning solvent and allow solvent to evaporate.
- If the material is an inactive metal or the cure speed is too slow, spray with Activator 3071 or 3049 and allow to dry.
- **For Slip Fitted Assemblies**, apply adhesive around the leading edge of the pin and the inside of the collar and use a rotating motion during assembly to ensure good coverage.
- **For Press Fitted Assemblies**, apply adhesive thoroughly to both bond surfaces and assemble at high press on rates.
- **For Shrink Fitted Assemblies** the adhesive should be coated onto the pin, the collar should then be heated to create sufficient clearance for free assembly.
- Parts should not be disturbed until sufficient handling strength is achieved.

### For Disassembly

- Apply localized heat to the assembly to approximately 250°C. Disassemble while hot.

## Storage:

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 46 °F to 82 °F. Please do not return any unused material to its original container.

**PRECAUTIONS:** This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**Warranty:** All products purchased from or supplied by Parson are subject to terms and conditions set out in the contract. Parson warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Parson is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Parson makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.